Application Serial No. 10/552,311

Filing Date: October 7, 2005

Docket: 294-229 PCT/US/RCE

Page 2 of 7

**AMENDMENTS TO THE CLAIMS** 

This listing of the claims replaces all prior versions and listings of claims in the

application.

Listing of the claims

1. (Currently amended) A method for reducing methane content in an off-gas

stream of a gas-fired plant, comprising contacting at least a portion of off-gas stream from

a gas-fired plant with a plasma and a catalyst wherein said off-gas stream is produced by

combustion of natural gas in a natural gas engine for combined heat and power generation

and wherein said plasma has a frequency below 1 kHz.

2. (Previously presented) A method according to claim 1, wherein NOx content

of said off-gas stream is reduced.

3. (Previously presented) A method according to claim 1, wherein said plasma is

generated by the use of an electrical or an electromagnetic field.

4. (Original) A method according to claim 3, wherein the plasma is generated by

use of an electrical field of 1-100 kV/cm.

5. (Cancelled)

6. (Previously presented) A method according to claim 1, wherein the plasma is

maintained with the aid of a partial discharge.

7. (Original) A method according to claim 6, wherein the partial discharge is

generated by use of a dielectric.

8. (Previously presented) A method according to claim 1, wherein the whole off-

gas stream or virtually the whole off-gas stream is contacted with said plasma and said

2

Application Serial No. 10/552,311

Filing Date: October 7, 2005 Docket: 294-229 PCT/US/RCE

Page 3 of 7

catalyst.

9. (Previously presented) A method according to claim 1, which is carried out at a

temperature of 300 - 500 °C.

10. (Previously presented) A method according to claim 1, wherein said catalyst

comprises Al<sub>2</sub>O<sub>3</sub>, zeolite, ZrO<sub>2</sub>, Ga<sub>2</sub>O<sub>3</sub>, TiO<sub>2</sub>, WO<sub>3</sub>, perovskite or combinations thereof.

11. (Original) A method according to claim 8, wherein said catalyst comprises  $\gamma$ -

 $Al_2O_{3.}$ 

12. (Previously presented) A method according to claim 1, wherein said catalyst is

a three-way catalyst, which comprises Rh, Pt or Pd on Al<sub>2</sub>O<sub>3</sub> support, if desired with

additions of Ce, La, Zr or Ce.

13. (Previously presented) A method according to claim 1, wherein said catalyst is

an oxidation catalyst, which comprises Ag or Pt on a metal oxide support.

14. (Currently amended) A method of reducing methane content in an off-gas stream

of a gas-fired plant comprising:

providing an off-gas stream produced from combustion of compressed natural gas in a

compressed natural gas engine for combined heat and power generation in a power plant,

wherein:

(1) a portion of the off-gas stream is passed through a plasma reactor connected to

a voltage source wherein said plasma has a frequency below 1 kHz; and

(2) the gas-stream <u>from the plasma reactor</u> is passed through a catalyst bed.

3